

# Quasiparticle States near the Surface and the Domain Wall in a $p_x \pm ip_y$ -Wave Superconductor

Masashige Matsumoto <sup>a,1</sup>, Manfred Sigrist <sup>b</sup>

<sup>a</sup>*Department of Physics, Faculty of Science, Shizuoka University, 836 Oya, Shizuoka 422-8529, Japan*

<sup>b</sup>*Yukawa Institute for Theoretical Physics, Kyoto University, Kyoto 606-8502, Japan*

---

## Abstract

The electronic states near a surface or a domain wall in the  $p_x \pm ip_y$ -wave superconductor are studied. This state has been recently suggested as the superconducting state of  $\text{Sr}_2\text{RuO}_4$ . The  $p_x \pm ip_y$ -wave pairing state breaks the time reversal symmetry and induces a magnetic field. The obtained temperature dependence of the magnetic field is consistent with the observed  $\mu\text{SR}$  data.

*Keywords:*  $p$ -wave superconductor; quasi-classical theory;  $\text{Sr}_2\text{RuO}_4$

---

Studying unconventional superconductors has become one of the most attractive problems in recent condensed matter research. They include the recently discovered  $\text{Sr}_2\text{RuO}_4$  [1]. Triplet pairing state of  $\mathbf{d}(\mathbf{k}) = (k_x \pm ik_y)\hat{z}$  is suggested as the d-vector [2]. Tunneling conductance for such pairing state has been examined finding that the conductance peak features related to the bound states are very sensitive to the angle of the incidence of the electron [3,4]. Recently we have studied quasiparticle properties at the surface or domain wall and reported that the local density of states at the surface is constant and does not show any peak-like or gap-like structure within the superconducting energy gap at low temperatures. While at the domain wall it is v-shaped and contains a small gap-like feature [5].

The intrinsic magnetism in the superconducting phase by  $\mu\text{SR}$  experiment indicates a pairing state with broken time reversal symmetry [6]. The magnetic field in the superconducting phase can be induced by surface, domain wall and impurity [7]. In this paper we examine the temperature dependence of the magnetic field induced near the surface and domain wall and compare them with the  $\mu\text{SR}$  experiment. For this purpose we use the same formulation as in our previous paper [5], which is based on the quasi-classical formulation developed by Schopohl *et al.* [8]. The spatial variation of the order parameter and vector potential can be determined self-consistently. For simplicity we assume a two-dimensional  $p_x + ip_y$  state. In Fig. 1 we show the magnetic field near a surface and a domain wall which is formed between  $p_x - ip_y$  and  $p_x + ip_y$  state. Near the  $T_c$  field maximum increases linearly with the decreasing the temperature and it satu-

---

<sup>1</sup> E-mail: spmmatu@ipc.shizuoka.ac.jp, Fax Number: 81-54-238-6352




Fig. 1. Induced magnetic field.  $B_c = \Phi_0 / 2\sqrt{2}\pi\xi_0\lambda_L$ ,  $\lambda_L$  is the London penetration depth and  $\Phi_0 = h/2e$ . (a) Spatial dependence at several temperatures.  $x$  is the distance from the surface or domain wall scaled by  $\xi_0 = v_F / \pi\Delta(0)$ , where  $\Delta(0)$  is the magnitude of the bulk order parameter at  $T=0$ . We chose a cutoff energy  $\omega_c = 20T_c$  and  $\kappa = \lambda_L / \xi_0 = 2.5$ . Temperatures scaled by  $T_c$  are depicted.  $B_z$  is antisymmetric under  $x \leftrightarrow -x$  for the domain wall. (b) Temperature dependence of the maximum  $|B_z/B_c|$ .

rates at low temperatures. This temperature dependence is qualitatively consistent with the  $\mu$ SR experiment. In the surface case the energy level of the bound state is estimated as  $\Delta_y(\mathbf{k}_F)$ , where  $\Delta_y(\mathbf{k}_F)$  is the  $p_y$ -component of the order parameter with momentum  $\mathbf{k}_F$ . Therefore, bound states in the region  $k_{Fy} < 0$  are occupied and yielding a spontaneous magnetic field, as long as they satisfy the condition  $T < |\Delta_y(\mathbf{k}_F)|$ .

An interesting magnetic property appears in the case of a  $p_x$  state. It has been pointed out that midgap state gives rise to a paramagnetic response [9–11]. Let us demonstrate it in the  $p_x$  state, which is suggested in the presence of the strong magnetic field in the  $x$  direction [12]. Figure 2 shows the spatial dependence of the paramagnetic field in the  $z$  direction. As it is studied in the  $d$ -wave case energy level of the midgap state shifts to  $ev_{Fy}A_y$ , which splits the zero bias conductance peak [10]. Here  $v_{Fy}$  and  $A_y$  are the  $y$ -component of Fermi velocity and vector potential, respectively. Note that  $A_y$  has the opposite sign of  $B_{\text{ext}}$ . Therefore, bound states in  $k_{Fy} > 0$  region are occupied for a positive  $B_{\text{ext}}$  and it generates a magnetic field parallel to  $B_{\text{ext}}$ . Bound states satisfying  $T < |ev_{Fy}A_y|$  contribute to the effect and the paramagnetic field rapidly decreases with the increase of temperature. In the real case, a small  $p_y$  part can be induced by  $B_{\text{ext}}$ .




Fig. 2. Spatial dependence of the magnetic field near the (1,0,0) surface for the  $p_x$  state at several temperatures. A small external field  $B_{\text{ext}} = 0.01B_c$  is applied in the  $z$  direction. Temperatures scaled by  $T_c$  are depicted.

The realized phase of the  $p_y$  component is such that generates a surface current which induces a field parallel to  $B_{\text{ext}}$ . This results in also the paramagnetic response. Without the strong field in the  $x$  direction, it is difficult to see this paramagnetic response, since the occupied bound states are already asymmetric under  $k_{Fy} \rightarrow -k_{Fy}$  and the state is difficult to modify with a small external field in the  $z$  direction.

This work was supported by Grant-in-Aid for Encouragement of Young Scientists from Japan Society for the Promotion of Science.

## References

- [1] Y. Maeno *et al.*, Nature **372** (1994) 532.
- [2] M. Sigrist *et al.*, in: Physics and Chemistry of Transition-Metal Oxides, (Springer, 1999).
- [3] C. Honerkamp and M. Sigrist, J. Low Temp. Phys. **111** (1998) 895.
- [4] M. Yamashiro, Y. Tanaka, Y. Tanuma and S. Kashiwaya, J. Phys. Soc. Jpn. **67** (1998) 3224.
- [5] M. Matsumoto and M. Sigrist, J. Phys. Soc. Jpn. **68** (1999) 994; erratum, *ibid.* 3120.
- [6] G. M. Luke *et al.*, Nature **394** (1998) 558.
- [7] M. Sigrist and K. Ueda, Rev. Mod. Phys. **63** (1991) 239.
- [8] N. Schopohl and K. Maki, Phys. Rev. B **52** (1995) 490.
- [9] S. Higashitani, J. Phys. Soc. Jpn. **66** (1997) 2556.
- [10] M. Fogelström, D. Rainer and J. A. Sauls, Phys. Rev. Lett. **79** (1997) 281.
- [11] H. Walter *et al.*, Phys. Rev. Lett. **80** (1998) 3598.
- [12] D. F. Agterberg, Phys. Rev. Lett. **80** (1998) 5184.